



TNE MEC


COLORBOOK




WHITES




00WH Tnemec White ▲
LRV 84%




06WH Albatross ▲
LRV 82%




07WH Winter Mist ▲
LRV 80%




08WH Acropolis ▲
LRV 72%




01WH Ash White ▲
LRV 84%




02WH Iceberg ▲
LRV 84%



03WH Daisy ▲
LRV 75%




04WH Silver Pearl ▲
LRV 76%




12WH Milkweed ▲
LRV 78%




13WH French Vanilla ▲
LRV 73%




14WH Veiled ▲
LRV 78%



15WH Aspen ▲
LRV 72%



15BR Pale ▲
LRV 83%



22BR Nova ▲
LRV 81%



57BR Cloud ▲
LRV 75%




79BR Coliseum ▲
LRV 67%

NOTE: Colors represented are digital reproductions of actual standards and will vary in appearance due to differences in monitor and video card output. These digital representations should not be used to finalize color selection(s). Please contact your local Tnemec Coatings Consultant for color-accurate samples or for assistance with suitable primer and finish coat selections and color matching.

LRV = Light Reflectance Value ▲ Standard color and gloss warranty is available in this color for Fluoronor and HydroFlon products. Other colors may be included. Contact your Tnemec representative for more information.

GRAYS



30GR Comet ▲
LRV 75%



24GR Lightpole ▲
LRV 62%



43GR Constellation ▲
LRV 71%



37GR Gradation ▲
LRV 65%



25GR Grey Day ▲
LRV 46%



31GR Slate Gray ▲
LRV 61%



57GR Aluminum ▲
LRV 46%



38GR Dove Gray ▲
LRV 58%



33GR Gray – ANSI No. 61 ▲
LRV 33%



32GR Light Gray – ANSI No. 70 ▲
LRV 44%



46GR Sinkler ▲
LRV 26%



39GR Pigeon ▲
LRV 42%




35GR Black ▲
LRV 4%



34GR Deep Space ▲
LRV 12%



48GR Moon Shadow ▲
LRV 10%




41GR Hammerhead ▲
LRV 17%


NOTE: Colors represented are digital reproductions of actual standards and will vary in appearance due to differences in monitor and video card output. These digital representations should not be used to finalize color selection(s). Please contact your local Tnemec Coatings Consultant for color-accurate samples or for assistance with suitable primer and finish coat selections and color matching.

LRV = Light Reflectance Value ▲ Standard color and gloss warranty is available in this color for Fluoronor and HydroFlon products. Other colors may be included. Contact your Tnemec representative for more information.


BLUES



57BL Steam ▲
LRV 76%



15BL Tank White ▲
LRV 83%




22BL Spring Rain ▲
LRV 76%



37BL Teardrop ▲
LRV 70%



59BL Seaspray ▲
LRV 55%



29BL Springwater ▲
LRV 75%



23BL Robin's Egg ▲
LRV 72%



39BL Delft Blue ▲
LRV 60%



61BL Blue Ribbon ▲
LRV 32%



09BL Cold Wind ▲
LRV 65%



25BL Fountainbleu ▲
LRV 50%



40BL Pika Blue ▲
LRV 41%



55BL Mysterious ▲
LRV 15%



11BL Canal Blue ▲
LRV 45%



26BL Clear Sky ▲
LRV 40%



41BL Lagoon ▲
LRV 24%



63BL Navy Blue ▲
LRV 9%



14BL Cadet Blue ▲
LRV 11%



28BL Pond
LRV 18%




42BL Blue Channel ▲
LRV 19%

NOTE: Colors represented are digital reproductions of actual standards and will vary in appearance due to differences in monitor and video card output. These digital representations should not be used to finalize color selection(s). Please contact your local Tnemec Coatings Consultant for color-accurate samples or for assistance with suitable primer and finish coat selections and color matching.

LRV = Light Reflectance Value ▲ Standard color and gloss warranty is available in this color for Fluoronor and HydroFlon products. Other colors may be included. Contact your Tnemec representative for more information.

GREENS



78GN Cumulus ▲
LRV 81%



92GN Marshall Green ▲
LRV 74%



106GN Bottle Green ▲
LRV 74%



51GN Sage ▲
LRV 72%



94GN Moonseed ▲
LRV 57%



108GN Ginger Mist ▲
LRV 58%



37GN Irish Spring ▲
LRV 71%



52GN Aztec Grass ▲
LRV 63%



96GN Zucchini ▲
LRV 27%



110GN Clover ▲
LRV 31%



10GN Aqua Sky ▲
LRV 71%



54GN Granny Smith ▲
LRV 38%



28GN Shannon's Isle ▲
LRV 13%



90GN Brahm Grass ▲
LRV 24%



13GN Mermaid ▲
LRV 29%



56GN Moss ▲
LRV 21%



21GN Fairway ▲
LRV 15%



91GN Balsam ▲
LRV 14%



14GN Bluegrass ▲
LRV 15%




112GN Foliage ▲
LRV 11%


NOTE: Colors represented are digital reproductions of actual standards and will vary in appearance due to differences in monitor and video card output. These digital representations should not be used to finalize color selection(s). Please contact your local Tnemec Coatings Consultant for color-accurate samples or for assistance with suitable primer and finish coat selections and color matching.

LRV = Light Reflectance Value ▲ Standard color and gloss warranty is available in this color for Fluoronor and HydroFlon products. Other colors may be included. Contact your Tnemec representative for more information.

BEIGES, TANS AND REDS



01BR Warm Sun ▲
LRV 78%



64BR Bisque ▲
LRV 82%



44BR Beige ▲
LRV 66%



10RD Barely Blush
LRV 64%



22YW Barbados ▲
LRV 72%



65BR Rock Slide ▲
LRV 67%



46BR Stable Brown ▲
LRV 46%



12RD Desert Rose
LRV 27%



03BR Washed Khaki ▲
LRV 61%



66BR Dust Bowl ▲
LRV 61%



05RD Hometown ▲
LRV 33%



14RD Red Clay ▲
LRV 14%




04BR Desert Sands ▲
LRV 51%



68BR Twine ▲
LRV 42%



23BR Sahara ▲
LRV 65%



07RD Terra Cotta ▲
LRV 11%



06BR Amber Canyon ▲
LRV 32%



70BR Worn Path ▲
LRV 16%



25BR Honey Roast ▲
LRV 48%




28RD Monterrey Tile
LRV 8%

NOTE: Colors represented are digital reproductions of actual standards and will vary in appearance due to differences in monitor and video card output. These digital representations should not be used to finalize color selection(s). Please contact your local Tnemec Coatings Consultant for color-accurate samples or for assistance with suitable primer and finish coat selections and color matching.

LRV = Light Reflectance Value ▲ Standard color and gloss warranty is available in this color for Fluoronor and HydroFlon products. Other colors may be included. Contact your Tnemec representative for more information.


BROWNS AND YELLOWS



50RD Bare Beige ▲
LRV 74%



72BR Sand Dunes ▲
LRV 70%



01YW Sunfresh ▲
LRV 84%



08YW Lemonwater ▲
LRV 84%



81BR Lumberg ▲
LRV 49%



74BR Clay ▲
LRV 48%



03YW Oat Straw ▲
LRV 73%



10YW Flaxseed ▲
LRV 80%



83BR Kindling ▲
LRV 20%



76BR Dried Timber ▲
LRV 22%




52BR Chamois ▲
LRV 62%



11YW Daffodil
LRV 76%



85BR Medium Bronze ▲
LRV 9%



77BR Coffee Grounds ▲
LRV 12%




53BR Tiki Wood ▲
LRV 46%



12YW Corncob
LRV 72%



86BR Dark Bronze ▲
LRV 6%



84BR Weathered Bark ▲
LRV 11%



62BR Acorn ▲
LRV 22%



05YW Grapefruit ▲
LRV 59%

NOTE: Colors represented are digital reproductions of actual standards and will vary in appearance due to differences in monitor and video card output. These digital representations should not be used to finalize color selection(s). Please contact your local Tnemec Coatings Consultant for color-accurate samples or for assistance with suitable primer and finish coat selections and color matching.

LRV = Light Reflectance Value ▲ Standard color and gloss warranty is available in this color for Fluoronor and HydroFlon products. Other colors may be included. Contact your Tnemec representative for more information.

BRIGHT AND SAFETY COLORS



14YW **Canary Yellow**
LRV 64%



04SF **Tangerine Orange/Safety**
LRV 29%



10SF **Deep Blue Sea** ▲
LRV 15%



14SF **Purple Rain/Safety**
LRV 17%



02SF **Lemon Yellow/Safety** ▲
LRV 53%



06SF **Candy Apple Red/Safety** ▲
LRV 14%



11SF **True Blue/Safety** ▲
LRV 18%



13SF **Purple Mountain's Majesty**
LRV 12%



03SF **Bright Yellow**
LRV 43%



07SF **Chilean Red**
LRV 9%



12SF **Purple Haze** ▲
LRV 8%



09SF **Spearmint Green/Safety** ▲
LRV 27%



05SF **International Orange**
LRV 17%



71RD **Old Glory Red**
LRV 16%



78BL **Old Glory Blue**
LRV 7%



08SF **Hunter Green** ▲
LRV 8%

NOTE: Colors represented are digital reproductions of actual standards and will vary in appearance due to differences in monitor and video card output. These digital representations should not be used to finalize color selection(s). Please contact your local Tnemec Coatings Consultant for color-accurate samples or for assistance with suitable primer and finish coat selections and color matching.

LRV = Light Reflectance Value ▲ Standard color and gloss warranty is available in this color for Fluoronor and HydroFlon products. Other colors may be included. Contact your Tnemec representative for more information.



Tnemec Company Incorporated 6800 Corporate Drive Kansas City, Missouri 64120-1372 1-800-TNEMEC1 Fax: 1-816-483-3969 www.tnemec.com

Published technical instructions and pricing are subject to change without notice. Contact your Tnemec technical representative for current technical data, instructions and pricing. Warranty information: The service life of Tnemec coatings will vary. For warranty, limitation of seller's liability and product information, please refer to Tnemec Product Data Sheets at www.tnemec.com or contact your Tnemec technical representative. Printed in the USA. ©Tnemec Company, Inc. 2008 CBOOK